

# Fast&Full

## Self-linking quick drying water-based pre-lacquer

Fast&Full is a self cross-linking acrylic based mono-component pre-lacquer providing a natural light effect to the wood; it is suitable for any wooden species. It can be easily sanded after 2 hours and enables to get a very smooth surface, enhancing the finish features. Overcoatable with all our water-based lacquers, Fast&Full has a low VOC content.

### Technical data at 20 °C and 60% R.H.

Aspetto	White liquid
Density	1,023 kg/l
pH	7,5 – 8,0
Dust dry	10 – 15 minutes
Touch dry	20 – 40 minutes
Overcoating	2 hours
Sanding	2 hours
Resa	10 – 12 m <sup>2</sup> /litre
Application temperature	> 10 °C – Frost sensitive
Storage	12 months in original closed packaging at temperature > 10 °C
VOC	50 g/litre, cat A/i (WB), limit 140 g/litre (2004/42/CE)
Tool cleaning	Clean the roller just after using it with water and neutral soap through a "squeezeroller", till the roller is clean, if possible rinse with clean water. Keep the rollers into Soluzione S/28 duly diluted with water, rinse with clean water before using them.
Available packaging	5 litre canister

### How to use

Sand the wood floor to obtain a smooth surface without oil, grease, wax or previous lacquers traces.

Fill the surface using a water-based filler like Idrostucco RS/30 or solvent-based like Lega Stucco RS/A mixed with wood dust; complete the sanding cycle with a 120 – 150 grit abrasive paper.

Vacuum and clean the wood floor carefully before applying Fast&Full. Always check that there are suitable conditions for lacquering.

Shake the drum and apply one coat of Fast & Full by roller or brush; the wood must be wet and the product uniformly spread.

Once dry, after 1 hour, sand carefully using a 180 – 220 grit abrasive paper, do not use finer grits. Clean the surface carefully.

Complete the lacquering with one of our water-based lacquers following the instructions on technical data sheets.



Varnishes &  
Finishing

## Fast&Full



### Certifications



**TOVER**<sup>®</sup>



Tover S.r.l.

Via Rosa Luxemburg, 2/A - Collegno (TO) - ITALY  
P. IVA 07783540011 - REA n. 920259  
Tel. +39/011.7792823 - Fax. +39/011.7792749  
www.tover.com - info@tover.com



## Notes

- In the case of thermowood or woods industrially aged with ammonia or other reagents, it is advisable to check the compatibility with the primer to ensure that there are no abnormal reactions or adhesion problems. The same attention should be observed in the case of oily or resinous woods, especially if not in common use.
- Frost sensitive
- Do not pour directly onto the floor.
- Use a suitable container.
- Avoid to apply the primer in two different times on the perimeter and the whole surface.
- Start with small outer segments and immediately treat the nearby areas.
- Avoid direct sun rays on the floor during application.
- Avoid air flows.
- Switch the heating off, above all under heating.
- Fast&Full must always be sanded.

## Safety norms

FOR PROFESSIONAL USE ONLY. Strictly respect the information reported on the label and consult the safety data sheet before using the product.

## Waste disposal

Dispose the not used product and empty containers in accordance with local in force regulations.

## Fast&Full



## Certifications



The information contained in this technical data sheet are for guidance only and they do not hold our responsibility. Adapt the use of our products to the environmental conditions and materials to be treated.  
Rev 06 – 24/05/2023. The current data sheet replaces the previous one.