

# Base Gold

## Two-component water-based primer with a moderately toning effect

Base Gold is a two-component water-based sealer with high coverage, capable of giving wood a light toning effect, more noticeable in exotic woods such as iroko, teak, or doussié. The impregnating properties of the product minimize the risk of overlapping; its excellent leveling, after sanding, leaves the surface smooth and uniform even in the presence of porous woods.

Base Gold is suitable with excellent results under any single- or two-component water-based lacquer or two-component solvent-based polyurethane lacquer.

### Technical Data (20 °C and 60% R.H.)

Appearance	Comp. A – White liquid Comp. B – Transparent liquid
Mix ratio	10:2
Mixture density	1.044 kg/litre
pH	7,0
Pot-life	4 hours
Dust-free time	30 minutes
Touch dry	2 hours
Sanding	12 - 18 hours
Possible dilution	Rallenty (max 5%) or water
Coverage	12 – 14 m <sup>2</sup> /litre
VOC	120 g/litre, cat A/j (WB), limit 140 g/litre (2004/42/CE)
Application temperature	+5 to +35 °C
Tool cleaning	Clean the roller immediately after use with water and neutral soap, using a roller wringer until no milky liquid is released; if possible, rinse again with clean water. Store rollers in properly diluted Soluzione S/28 cleaning solution; rinse with clean water before reuse.
Storage	12 months in original sealed packaging – Protect from frost
Packaging	Plastic cans of 5 + 1 litres

### Application Instructions

Sand the parquet to obtain a smooth surface free from oils, greases, waxes, or old treatments. Fill and level the surface using a water-based filler like Idrostucco RS/30 or solvent-based Lega Stucco RS/A mixed with wood dust; complete the sanding cycle with 120–150 grit. Vacuum and thoroughly clean the parquet before applying the product. Always verify suitable conditions for varnishing. Shake the can well, mix the two components in the exact mixing ratio and apply one coat of Base Gold using a roller or brush, making sure to wet the wood evenly. After 12–18 hours, proceed with sanding using a 180–220 grit mesh. Clean the surface thoroughly. Complete the varnishing cycle with one of our water-based lacquers following the instructions in the relevant technical data sheets.



LACQUERS &  
FINISHES



### CERTIFICATIONS



Base Gold can also be overcoated with solvent-based polyurethane lacquers; in this case, wait at least 24 hours before overcoating.

## Notes

- For thermo-treated or industrially aged woods with ammonia or other reagents, verify compatibility with the sealer to ensure there are no abnormal reactions or adhesion problems.
- Protect from frost.
- Avoid varnishing the perimeter and the entire room in two steps.
- Apply within the 4-hour pot life to obtain a uniform film.
- Do not pour it directly onto the floor.
- Use a suitable container.
- Avoid direct sunlight, drafts, and heating during application.

## Safety Regulations

Product for professional use. Strictly follow the labeling instructions and consult the safety data sheets before use.

## Disposal

Dispose of unused product and empty containers in accordance with current local regulations.



## LACQUERS & FINISHES



## CERTIFICATIONS



The recommendations in this technical bulletin are provided for informational purposes only and do not imply any responsibility on our part, as the methods and conditions of use are beyond our control. We recommend verifying the actual suitability for the intended use. Rev 04 – 20/07/2021. This sheet cancels and replaces the previous version.